

TIPO SCHIUMA	DENSITÀ	PORTANZA	CARICO A ROTTURA	ALLUNGAMENTO A ROTTURA	CELLE/cm	ALTRO OTHER
TYPE	DENSITY	HARDNESS	TENSILE STRENGTH	TENSILE ELONGATION	CELLS/cm	
	kg/m ³	kPa	kPa (min.)	% min	nr/cm	
METODO / METHOD	ISO 845	ISO 3386	ISO 1789	ISO 1789	TG	

ESTERE / ESTER

R20	19 - 21	4 - 5,5	140	150	12 - 16	OEKO TEX STD 100, class 1
RR20	19 - 21	4 - 6	100	150	12 - 16	OEKO TEX STD 100, class 1
RR20/R	19 - 21	5 - 8	100	100	12 - 16	OEKO TEX STD 100, class 1
RR24	22,5 - 25,5	4 - 6	100	120	10 - 14	OEKO TEX STD 100, class 1
SR20/A	19-21,5	5 - 7	120	100	12 - 16	OEKO TEX STD 100, class 1
SR20/N	19 - 21	Min. 150 gr/cm ² Rigidezza Fiat 9.55260/ Hardness acc. Fiat	100	80	14 - 18	OEKO TEX STD 100, class 1
SR26	24 - 27	Min. 120 gr/cm ² Rigidezza Fiat 9.55260/ Hardness acc. Fiat	100	60	12 - 16	OEKO TEX STD 100, class 1
SR26/N	24 - 28	Min. 200 gr/cm ² Rigidezza Fiat 9.55260/ Hardness acc. Fiat	100	60	12 - 16	OEKO TEX STD 100, class 1
SR28	26 - 30	Min. 225 gr/cm ² Rigidezza Fiat 9.55260/ Hardness acc. Fiat	150	60	14 - 18	OEKO TEX STD 100, class 1
CO20	19 - 22	3 - 5	150	180	15 - 19	OEKO TEX STD 100, class 1
CO20NF	18,5 - 21,5	2 - 5	120	200	18 - 22	OEKO TEX STD 100, class 1
CO24/P	22,5 - 25,5	3 - 5	150	150	15 - 19	OEKO TEX STD 100, class 1
CO30	29 - 32	3 - 5	150	150	15 - 19	OEKO TEX STD 100, class 1
N32	28 - 31	3,5 - 5,5	120	150	12 - 15	OEKO TEX STD 100, class 1
N45	40 - 45	4 - 6	130	150	16 - 20	OEKO TEX STD 100, class 1
N55	52 - 58	4,5 - 6,5	100	150	16 - 20	OEKO TEX STD 100, class 1



Toscana Gomma

www.toscanagomma.it

AZIENDA CERTIFICATA / CERTIFIED COMPANY

IATF 16949 • First edition 2016-10-01 Certificate: 0314869

OHSAS 18001:2007 • Code IAF 14

ISO 9001:2015 • Certificate: 50 100 3596 - Rev. 007



CERTIFICAZIONI CERTIFICATION



OEKO-TEX®
Standard 100
Certificate No.: 070959.0
